



PREMIUM LEAD-FREE SOLDER

Meets Highest Product Standards

- NSF 61 Certification for safe use in potable water applications

100% Environmentally Safe

- Completely free of antimony or nickel



Sterling Lead-Free

- Lowest melting temperature: 410° F
- Highest tensile strength: 7130 psi
- Best flowing lead-free solder available
- Formula advantages



WOR PROD NO	DESCRIPTION	WEIGHT		DIAMETER		CARTON QTY.
		LB.	G.	IN.	MM.	
331755	Sterling Wire Spool	1	454	.118	3	50
331842*	Sterling Wire Spool	1	454	.118	3	50
331841	Sterling Wire Spool	1	454	.118	3	20
331843	Sterling Wire Spool	1	454	.062	1.6	50
331897	Sterling Wire Spool	1/4	113	.118	3	50
331896	Sterling Wire Spool	1/2	227	.118	3	50
331898	Sterling Wire Spool	5	2270	.118	3	10
331895	Sterling Wire Spool	5	2270	.062	1.6	10
331899	Sterling Sm Ingot	5	2270	—	—	10

*Spool is not sold in an individual box



Premium Silver Lead-Free

- Low melting temperature: 440° F
- High tensile strength: 6900 psi
- Ideal for use on large diameter pipe
- Wide pasty range (440°–640° F) allows for more working time



WOR PROD NO	DESCRIPTION	WEIGHT		DIAMETER		CARTON QTY.
		LB.	G.	IN.	MM.	
331756	Silver Wire Spool	1	454	.118	3	50
331859*	Silver Wire Spool	1	454	.118	3	50
331844	Silver Wire Spool	1	454	.118	3	20
331900	Silver Wire Spool	1/4	113	.118	3	50

*Spool is not sold in an individual box



Select Lead-Free

- Low melting temperature: 419° F
- High tensile strength: 6950 psi
- Increased flow properties
- Formula advantages



WOR PROD NO	DESCRIPTION	WEIGHT		DIAMETER		CARTON QTY.
		LB.	G.	IN.	MM.	
331754	Lead-Free Wire Spool	1	454	.118	3	50
331838*	Lead-Free Wire Spool	1	454	.118	3	50
331836	Lead-Free Wire Spool	1	454	.093	2.4	50
331894	Lead-Free Wire Spool	1/4	113	.118	3	50
331893	Lead-Free Wire Spool	1/2	227	.118	3	50

*Spool is not sold in an individual box

Made in the USA WITH GLOBAL COMPONENTS